

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## Group Number Assessment

(In accordance with AS 5637.1-2015)

This is to confirm that the product as described below has been tested by AWTA Product Testing .


Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

As per AS 5637.1 Clause 9(n) it was valid to test this particular material / system in the cone calorimeter for the assignment of a NCC Group Number.

**Test Sponsor :** Australian Panels  
2 Wella Way  
Somersby NSW 2250

**Test Number :** 24-002490  
**Issue Date :** 17/07/2024  
**Print Date :** 17/07/2024

**Sponsor Product :** Clients Ref : "Easycraft Silhouette"  
Rigid Panel  
Colour : Sand  
End Use : Wall Lining  
Nominal Composition : Primed MDF, water based paint, wood fibre/resin/wax  
Nominal Mass per Unit Area/Density : 770kg/m3  
Nominal Thickness : 16mm



71616

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. Its transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, its disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## Group Number Assessment

(In accordance with AS 5637.1-2015)

This is to confirm that the product as described below has been tested by AWTA Product Testing .

Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

As per AS 5637.1 Clause 9(n) it was valid to test this particular material / system in the cone calorimeter for the assignment of a NCC Group Number.

---

<b>Test Sponsor :</b>	Australian Panels 2 Wella Way Somersby NSW 2250	<b>Test Number :</b>	24-002490
		<b>Issue Date :</b>	17/07/2024
		<b>Print Date :</b>	17/07/2024

---

Product Group Number Classification : 3

Average Specific Extinction Area : 26.9 m<sup>2</sup>/kg



Chris Campbell  
Client Relations Manager

71616

---

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. It's transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, it's disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.